

alwado



NATURAL STATE OF WOOD “ALWADO LAMINATED BEAM”

ALWADO LAMINATED BEAM

The **ALWADO** brand is incorporated by Alanyalı Ahşap with a monthly production of Laminated Beam of 500 m³, Wall Profile, Woodworking Profile and Constructional Profile (A-20) in the Antalya integrated facilities. It serves products of good quality to the Turkish constructional wood market with an innovator and fast perception of service.

PROPERTIES

| | |
|--------------------------|---|
| <u>Tree Species</u> | Spruce - Pine |
| <u>Cementing Quality</u> | Conforming EN 14080 Standards with PURBOND HB S309 Polyurethane glue. |
| <u>Measurements (mm)</u> | Thickness ; 50,65,80,100,135,160,185 Wideness ; 90,100,120,135,140,160,170, 210, 300 Length ; 6000, 9000,12000,13500 |
| <u>Weight</u> | 450-500 kg/m ³ |
| <u>Moisture Content</u> | %12 ± 2 |
| <u>Packaging</u> | Packaged with stretch packages as pallets |
| <u>Properties</u> | The products are clear of knots and defects. The products have been finger jointed. The products have been pressed under the pressure of 11.000 kg/cm ² in the Laminated Wood press. |



CURVILINEAR LAMINATED BEAM

PROPERTIES

| | |
|--------------------------|---|
| Tree Species | Spruce – Pinewood |
| Cementing Quality | Conforming EN 14080 Standards with PURBOND HB S309 Polyurethane glue. |
| Measurements | Thickness ; 50,65,80,100,135,160 Wideness ; 90,100,120,135,140, 160,170, 210, 300 Length; 6000, 9000,12000,13500 |
| Weight | 450-500 kg/m ³ |
| Moisture Content | %12 ± 2 |
| Packaging | Packaged with stretch packages as pallets. |
| Properties | The products are clear of knots and defects. The products have been finger jointed. The products have been pressed under the pressure of 11.000 kg/cm ² in the Laminated Wood press. |



WALL PROFILED

PROPERTIES

| | |
|--------------------------|---|
| Tree Species | Spruce - Pine |
| Cementing Quality | Conforming EN 14080 Standards with PURBOND HB S309 Polyurethane glue. |
| Measurements | Thickness ; 40, 80,120 Wideness ; 140 Length ; 6000, 9000,12000 |
| Weight | 450-500 kg/m ³ |
| Moisture Content | %12 ± 2 |
| Packaging | Packaged with stretch packages as pallets. |
| Properties | The products are clear of knots and defects. The products have been finger jointed. The products have been pressed under the pressure of 11.000 kg/cm ² in the Laminated Wood press. |



alwado[®]
ALANYALI AHSAP transforest

Antalya Factory: Organize Sanayi Bölgesi 2.Kısım 23.Cad. No:3 Antalya / TURKEY- Tel : +90 242 258 18 58 Fax: +90 242 258 10 55

www.alwado.com.tr info@alwado.com.tr facebook.com/alwado.com.tr twitter.com/alwado.com.tr instagram/alwado.com.tr